Printing date 22.01.2019

Version number 12

Revision: 22.01.2019

· 1.1 Product identifier	bstance/mixture and of the company/undertaking
· Product name LOBASOL Markant/Markant	Color
• Article number: 10508 • 1.2 Relevant identified uses of the substance No further relevant information available. • Application of the substance / the mixture Co	5
• 1.3 Details of the supplier of the safety data s • Manufacturer/Supplier: LOBA GmbH & Co. KG Leonberger Straße 56 - 62 D-71254 Ditzingen	Tel.: +49 (0)7156/357-0
· Informing department:	
Productmanagement e-mail: service@loba.de	

• **1.4 Emergency telephone number:** Emergency CONTACT (24-Hour-Number):GBK GmbH +49 (0)6132-84463

SECTION 2: Hazards identification

• 2.1 Classification of the substance or mixture • Classification according to Regulation (EC) No 1272/2008 The product is not classified, according to the CLP regulation.

· 2.2 Label elements

- · Labelling according to Regulation (EC) No 1272/2008 Void
- · Hazard pictograms Void
- · Signal word Void
- · Hazard statements Void
- · Precautionary statements
- P273 Avoid release to the environment.
- Additional information:

EUH208 Contains Fettsäuren C 18 unges., Reaktionsproodukt mit N,N Dimethyl-1,3-propanediamin, 2-butanone oxime, cobalt(II) 2-ethylhexanoate. May produce an allergic reaction.

EUH210 Safety data sheet available on request.

- · 2.3 Other hazards
- · Results of PBT and vPvB assessment
- · **PBT:** Not applicable.
- · vPvB: Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Chemical characterisation: Mixtures

• Description: Mixture of the substances listed below with harmless additions.

· Dangerous components:		
EC number: 918-481-9	<i>Hydrocarbons, C10-C13, n-alkanes, isoalkanes, cyclics,</i> $< 2\%$ <i>aromatics</i>	25-50%
Reg.nr.: 01-2119457273-39	🚸 Asp. Tox. 1, H304	
• Additional information For	the wording of the listed hazard phrases refer to section 16.	

(Contd. on page 2)

Printing date 22.01.2019

Version number 12

Revision: 22.01.2019

Product name LOBASOL Markant/Markant Color

(Contd. of page 1)

SECTION 4: First aid measures

- 4.1 Description of first aid measures
- · General information No special measures required.
- After inhalation Supply fresh air; consult doctor in case of symptoms.
- · After skin contact The product is not skin irritating.
- · After eye contact Rinse opened eye for several minutes under running water.
- · After swallowing In case of persistent symptoms consult doctor.
- · 4.2 Most important symptoms and effects, both acute and delayed No further relevant information available.
- + 4.3 Indication of any immediate medical attention and special treatment needed
- No further relevant information available.

SECTION 5: Firefighting measures

- · 5.1 Extinguishing media
- · Suitable extinguishing agents
- CO2, extinguishing powder or water jet. Fight larger fires with water jet or alcohol-resistant foam.
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.
- 5.3 Advice for firefighters
- · Protective equipment: No special measures required.

SECTION 6: Accidental release measures

- 6.1 Personal precautions, protective equipment and emergency procedures Not required.
- 6.2 Environmental precautions: Do not allow product to reach sewage system or water bodies. Inform respective authorities in case product reaches water or sewage system.
- 6.3 Methods and material for containment and cleaning up:
- Absorb with liquid-binding material (sand, diatomite, acid binders, universal binders, sawdust).
- 6.4 Reference to other sections
- See Section 7 for information on safe handling
- See Section 8 for information on personal protection equipment.
- See Section 13 for information on disposal.

SECTION 7: Handling and storage

- · 7.1 Precautions for safe handling No special measures required.
- Information about protection against explosions and fires: No special measures required.
- · 7.2 Conditions for safe storage, including any incompatibilities
- · Storage
- Requirements to be met by storerooms and containers: No special requirements.
- Information about storage in one common storage facility: Not required.
- Further information about storage conditions: None.
- Storage class 10
- 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

• Additional information about design of technical systems: No further data; see item 7.

(Contd. on page 3)

GB

Printing date 22.01.2019

*

Version number 12

Revision: 22.01.2019

Product name LOBASOL Markant/Markant Color

 Components with critical values that require monitoring at the workplace: The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. Additional information: The lists that were valid during the compilation were used as basis. 8.2 Exposure controls Personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Breathing equipment: Not required. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material: ≥ 0.04 mm Penetration time of glove material Material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). 	(Contd. of page 2)
The product does not contain any relevant quantities of materials with critical values that have to be monitored at the workplace. • Additional information: The lists that were valid during the compilation were used as basis. • Additional information: The lists that were valid during the compilation were used as basis. • Additional information: The lists that were valid during the compilation were used as basis. • Additional protective equipment • General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. • Breathing equipment: Not required. • Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation • Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm • Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	· 8.1 Control parameters
 Personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Breathing equipment: Not required. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6 	The product does not contain any relevant quantities of materials with critical values that have to be monitored at
 Personal protective equipment General protective and hygienic measures The usual precautionary measures should be adhered to in handling the chemicals. Breathing equipment: Not required. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6 	· 8.2 Exposure controls
The usual precautionary measures should be adhered to in handling the chemicals. Breathing equipment: Not required. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	· Personal protective equipment
 Breathing equipment: Not required. Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6 	
• Protection of hands: The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation • Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm • Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
The glove material has to be impermeable and resistant to the product/ the substance/ the preparation. Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
Nitrile rubber, NBR The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	· Material of gloves
varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Recommended thickness of the material: ≥ 0.04 mm Penetration time of glove material The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	Nitrile rubber, NBR
The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application.
observed. For the mixture of chemicals mentioned below the penetration time has to be at least 480 minutes (Permeation according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
according to EN 374 Part 3: Level 6). Value for the permeation: Level ≤ 6	
Value for the permeation: Level ≤ 6	
• Eye protection: Safety glasses recommended during refilling.	• Eye protection: Safety glasses recommended during refilling.

9.1 Information on basic physical ar General Information	nd chemical properties	
Appearance:		
Form:	Fluid	
Colour:	Brown	
Smell:	Recognisable	
Odour threshold:	Not determined.	
pH-value:	Not determined.	
Change in condition Melting point/freezing point: Initial boiling point and boiling ra	Not determined nge: 130 °C	
Flash point:	65 °C	
Inflammability (solid, gaseous)	Not applicable.	
Decomposition temperature:	Not determined.	
Self-inflammability:	Product is not selfigniting.	
Explosive properties:	Product is not explosive.	
Lower:	Not determined.	
Upper:	Not determined.	

Printing date 22.01.2019

Version number 12

Revision: 22.01.2019

Product name LOBASOL Markant/Markant Color

		(Contd. of page
· Steam pressure:	Not determined.	
· Density at 20 °C	$0.904 \ g/cm^3$	
· Relative density	Not determined.	
· Vapour density	Not determined.	
· Evaporation rate	Not determined.	
· Solubility in / Miscibility with		
Water:	Not miscible or difficult to mix	
· Partition coefficient: n-octanol/water:	Not determined.	
· Viscosity:		
dynamic at 20 °C:	264 mPas	
kinematic:	Not determined.	
• 9.2 Other information	No further relevant information available.	

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

- · 10.2 Chemical stability
- Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.
- 10.3 Possibility of hazardous reactions No dangerous reactions known
- 10.4 Conditions to avoid No further relevant information available.
- 10.5 Incompatible materials: No further relevant information available.
- 10.6 Hazardous decomposition products: No dangerous decomposition products known

SECTION 11: Toxicological information

· 11.1 Information on toxicological effects

- Acute toxicity Based on available data, the classification criteria are not met.
- · Primary irritant effect:
- Skin corrosion/irritation Based on available data, the classification criteria are not met.
- Serious eye damage/irritation Based on available data, the classification criteria are not met.
- Respiratory or skin sensitisation Based on available data, the classification criteria are not met.
- · CMR effects (carcinogenity, mutagenicity and toxicity for reproduction)
- · Germ cell mutagenicity Based on available data, the classification criteria are not met.
- · Carcinogenicity Based on available data, the classification criteria are not met.
- Reproductive toxicity Based on available data, the classification criteria are not met.
- STOT-single exposure Based on available data, the classification criteria are not met.
- STOT-repeated exposure Based on available data, the classification criteria are not met.
- Aspiration hazard Based on available data, the classification criteria are not met.

SECTION 12: Ecological information

· 12.1 Toxicity

- · Aquatic toxicity: No further relevant information available.
- 12.2 Persistence and degradability No further relevant information available.
- 12.3 Bioaccumulative potential No further relevant information available.
- · 12.4 Mobility in soil No further relevant information available.

(Contd. on page 5)

GB

Printing date 22.01.2019

Version number 12

Revision: 22.01.2019

(Contd. of page 4)

Product name LOBASOL Markant/Markant Color

• Additional ecological information:

• General notes:

Water hazard class 1 (Self-assessment): slightly hazardous for water.

Do not allow undiluted product or large quantities of it to reach ground water, water bodies or sewage system.

· 12.5 Results of PBT and vPvB assessment

• *PBT:* Not applicable.

• **vPvB:** Not applicable.

• 12.6 Other adverse effects No further relevant information available.

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

After prior treatment product has to be landfilled or incinerated under adherence to the regulations pertaining to the disposal of especially hazardous waste.

· European waste catalogue

08 00 00 WASTES FROM THE MANUFACTURE, FORMULATION, SUPPLY AND USE (MFSU) OF COATINGS (PAINTS, VARNISHES AND VITREOUS ENAMELS), ADHESIVES, SEALANTS AND PRINTING INKS

08 01 00 wastes from MFSU and removal of paint and varnish

08 01 11* waste paint and varnish containing organic solvents or other hazardous substances

· Uncleaned packagings:

• *Recommendation: Disposal must be made according to official regulations.*

14.1 UN-Number ADR, ADN, IMDG, IATA	Void	
14.2 UN proper shipping name ADR, ADN, IMDG, IATA	Void	
14.3 Transport hazard class(es)		
ADR, ADN, IMDG, IATA Class	Void	
14.4 Packing group ADR, IMDG, IATA	Void	
14.5 Environmental hazards: Marine pollutant:	No	
14.6 Special precautions for user	Not applicable.	
14.7 Transport in bulk according to Ann Marpol and the IBC Code	ex II of Not applicable.	
UN "Model Regulation":	Void	

(Contd. on page 6)

Printing date 22.01.2019

Version number 12

Revision: 22.01.2019

Product name LOBASOL Markant/Markant Color

(Contd. of page 5)

SECTION 15: Regulatory information

· 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture

- · Directive 2012/18/EU
- · Named dangerous substances ANNEX I None of the ingredients is listed.
- · National regulations
- · Water hazard class: Water hazard class 1 (Self-assessment): slightly hazardous for water.
- 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

These data are based on our present knowledge. However, they shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

Alteration in the context will be marked with a cross (*).

· Relevant phrases

H304 May be fatal if swallowed and enters airways.

- · Department issuing data specification sheet: Productmanagement.
- · Contact: Dr W. Ehmann
- Abbreviations and acronyms: RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer (Regulations Concerning the International Transport of Dangerous Goods by Rail) ICAO: International Civil Aviation Organisation ADR: Accord européen sur le transport des marchandises dangereuses par Route (European Agreement concerning the International Carriage of Dangerous Goods by Road) IMDG: International Maritime Code for Dangerous Goods IATA: International Air Transport Association GHS: Globally Harmonised System of Classification and Labelling of Chemicals EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances CAS: Chemical Abstracts Service (division of the American Chemical Society) PBT: Persistent, Bioaccumulative and Toxic vPvB: very Persistent and very Bioaccumulative Asp. Tox. 1: Aspiration hazard - Category 1 • * Data compared to the previous version altered.