

WAKOL D 3035 Dispersion Primer

Technical Information

Area of application

Ready-to-use dispersion-based primer for priming

- cement, calcium sulphate, cast asphalt concrete
- concrete subfloors
- magnesite screed with exclusively mineral-based additives
- thoroughly cleaned tiles, terrazzo
- wood planks, gypsum fibre boards
- water resistant adhesive residues

before subsequent levelling indoors.

Special properties



1)



2)

- solvent-free according to the definition of the TRGS 610
- suitable for chairs with castors
- suitable over underfloor heating

1) based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMICODE EC1 PLUS: very low in emissions

2) Emission class according to French law

Technical data

Raw material base:	polyacrylate dispersion
Drying time:	on cement paving and concrete subfloors following visible drying; on cast asphalt concrete, tiles, terrazzo and water resistant adhesive residues at least 60 min.;; on calcium sulphate concrete, magnesite screed, wood planks and gypsum fibre boards 2 - 4 hours
Cleaning agent:	water before adhesive dries
Storage time:	12 months at room temperature
Storage temperature:	not below +5 °C, sensitive to frost
GISCODE:	D1

EMICODE: EC1 PLUS

Application and consumption³⁾:

WAKOL Primer Roller, short-haired velour or foam roller ca. 100 - 150 g/m²

3) Consumption is dependent on surface structure and absorbability of subfloor

Subfloors

The subfloor and the climatic conditions of the room must meet the requirements of DIN 18356 or 18365. Subfloors must be permanently dry, solid, and free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Mechanically pretreat and thoroughly vacuum-clean calcium-sulphate-based screeds according to manufacturer's specifications or according to the currently applicable standards and codes.

Usage

Shake primer well before using. Apply WAKOL D 3035 Dispersion Primer with WAKOL Primer Roller, velour or foam roller on the subfloor, avoiding puddle formation. Subsequent levelling operations after the primer has completely dried; pay careful attention to drying times.

Important

Processing not below floor temperature of +15 °C and room temperature of +18 °C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %.

In cold weather, warm up WAKOL D 3035 Dispersion Primer in due time in heated room.

All information is based on approx. 20 °C and 65 % relative air humidity.

Do not use WAKOL D 3035 Dispersion Primer on magnesite screeds with organic additives (stonewood screeds) and wooden material tiles.

Do not use WAKOL D 3035 Dispersion Primer directly under parquet adhesives.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardised conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the currently applicable codes must be observed. We gladly provide technical advice.

The product data sheets can be found in their latest version at www.wakol.com.

This Technical Information of 15.08.2017 supersedes all previous versions.