FLOORING ADHESIVE FOR DIRECT ADHESION TO EXISTING SUBFLOOR

ASSUMPTIONS	PLY	CHIPBOARD	CONCRETE	OSB	ADHESIVE & BITUMEN RESIDUES
	Ply should be secured to the surface below. It should be of high quality and free from contaminants and debris. If needed it can be abraded and sealed with WAKOL PU280.	Chipboard may need to be abraded if impregnated with ADHESIVE resistant product or to form a key. Ensure chipboard is secured to the surface below.	WAKOL PU280 ONE COAT IF PRIMER IS REQUIRED or WAKOL PU280 X 2 COATS as a moisture suppressant.	OSB must be secured to the surface below. It may have to be abraded if it contains an adhesive inhibitor or contaminants. If abraded it can be primed with WAKOL PU280.	All loose adhesive, bitumen Residue should be removed. Once secure, the surface sould be abraded before applying a Primer, DPM or adhesive. WAKOL PU280 IN 1 or 2 COATS **ONLY ABRADE IF ASBESTOS IS NOT CONTAINED IN SUBFLOOR!**
Concrete only NO UNDERFLOOR HEATING RH Reading between 75% and 95%					
Concrete WITH UNDERFLOOR HEATING RH Reading less than 65%					
PRODUCTS					
PRIMERS					
WAKOL PU280 PRIMER 1 COAT	IF REQUIRED. Yes after abrasion	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED
WAKOL PU280 MOISTURE SUPPRESANT 2 COATS			Yes IF REQUIRED		Yes IF REQUIRED
WAKOL MS330 MOISTURE SUPRESSANT 1 COAT			Yes IF REQUIRED		Yes IF REQUIRED
WAKOL D3055 UNIVERSAL PARQUET PRIMER	IF REQUIRED. Yes after abrasion	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED	IF REQUIRED. Yes after abrasion	
ADHESIVES					
LECOL 5500 SOLVENT ADHESIVE			Engineered and Solid		
WAKOL MS230 (TROWEL)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)
WAKOL MS260 (TROWEL)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)
WAKOL MS262 LIQUID BATTEN	Engineered only	Engineered only	Engineered only	Engineered only	Engineered only

ASSUMPTIONS	ASPHALT	MILD STEEL	ANHYDRITE	THERMOPLASTIC TILES	CERAMIC
	Asphalt will need to be made secure and abraded before applying a primer and adhesive. We advise to use of WAKOL D3045 Primer and WAKOL Z715 Levelling compound to get the best results. **No abrading can take place if Asbestos is present!!**	All Steel needs to be de-greased before an adhesive can be used. All metalic surfaces need to be secure and not offer excessive movement.	Gypsum screed will often need to be abraded then primed but not sealed with a DPM! **WAKOL PU280 IN ONE COAT ONLY!!!! OR WAKOL D3055**	**Thermoplastic tiles should be removed.** If they are secure they need to be abraded before applying a DPM or Primer. WAKOL PU280 IN ONE COAT. **No abrading can take place if asbestos is present!**	Ceramics will need to be cleaned with WAKOL R4515 tile cleaner and subsequently abraded until surface scratches are clearly visible, never apply any primer before adhering directly to the creamic surface!
Concrete only NO UNDERFLOOR HEATING RH Reading between 75% and 95%					
Concrete WITH UNDERFLOOR HEATING RH Reading less than 65%					
PRODUCTS					
PRIMERS					
WAKOL PU280 PRIMER 1 COAT	IF REQUIRED. Yes after abrasion	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED
WAKOL PU280 MOISTURE SUPPRESANT 2 COATS			Yes IF REQUIRED		Yes IF REQUIRED
WAKOL MS330 MOISTURE SUPRESSANT 1 COAT			Yes IF REQUIRED		Yes IF REQUIRED
WAKOL D3055 UNIVERSAL PARQUET PRIMER	IF REQUIRED. Yes after abrasion	IF REQUIRED. Yes after abrasion	Yes IF REQUIRED	IF REQUIRED. Yes after abrasion	
ADHESIVES					
LECOL 5500 SOLVENT ADHESIVE			Engineered and Solid		
WAKOL MS230 (TROWEL)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)	Engineered and Small solid (under 25mm thick / 130mm wide)
WAKOL MS260 (TROWEL)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)	Engineered and Solid (under 25mm thick / 200mm wide)
WAKOL MS262 LIQUID BATTEN	Engineered only	Engineered only	Engineered only	Engineered only	Engineered only