

WAKOL Z 626 Levelling Compound

Technical Information

Area of application

Low-tension, cement-based levelling compound for smoothing out unevenness in layers 2 - 20 mm thick underneath

- Textile flooring
- Elastic flooring
- Parquet (minimum 3 mm thickness required)
- Cork flooring

indoors.

Special properties



- chromate reduced according to REACH
- suitable for chair castors
- suitable for direct use in conjunction with surface treatment
- can be applied with a rake
- self-levelling
- can be pumped
- suitable for heavy loads from a layer thickness of 3 mm

- 1) Based on the criteria of GEV (Association for Emission-controlled Laying Materials), classified as EMI CODE EC1 PLUS: very low in emissions
- 2) Emissions class according to French law
- 3) Cement-based products, low chromate
- 4) Meets the requirements of the European Community
- 5) Suitable for underfloor heating
- 6) Suitable for exposure to castor wheels

Technical data

Raw material base:	Special cement/quartz mixture with special plastic additives
Strength of coating:	up to 20 mm
Mixture:	approx. 5,25 – 5,5 l water + 22 kg WAKOL Z 626
Processing time:	approx. 25 minutes

Suitable for walking: after approx. 2 hours
Waiting time before laying: up to 5 mm layer thickness, after 6 hours
up to 10 mm layer thickness, after 12 hours up to 20 mm layer thickness, after 24 hours
Storage time: 12 months; store in a cool and dry location, tightly seal any opened bags and use as soon as possible
Application and consumption⁷⁾:

Trowel, approx. 1,5 g/m² layer thickness
Rake

7) Consumption is dependent on surface structure and absorbability of subfloor

Subfloors

The subfloor as well as the room climate conditions must meet the requirements of the applicable standards and data sheets. Subfloors must be permanently dry, solid, level, free from cracks, dirt and adhesion-inhibiting substances. Use a suitable mechanical procedure to remove separating layers.

Prime cement paving, calcium sulphate concrete, concrete and other absorbent subfloors with WAKOL D 3004 Primer Concentrate, diluted 1:2 with water, or with WAKOL D 3003 Dispersion Primer. Always comply with primer drying times.

New, well sanded, standardised cast asphalt concrete does not require a primer. Prime used and poorly sanded mastic asphalt concrete as per the relevant standard, and prime old subfloors that have old, waterproof adhesive residues with WAKOL D 3004 Primer Concentrate, diluted with water at a ratio of 1:1, or with WAKOL D 3003 Dispersion Primer.

On wooden subfloors use WAKOL D 3045 Special Primer or WAKOL D 3004 Primer Concentrate.

Usage

Stir WAKOL Z 626 Levelling Compound in a clean stirring vessel with approx. 5,25 – 5,5 l clear, cold tap water until free of lumps. The mixing device must not exceed 600 rpm. Leave the compound to stand for approx. 1 minute before briefly mixing it again.

Apply stirred compound with dripper, smoothing trowel or knife uniformly to the subfloor in the desired layer thickness. Before applying the levelling compound, check whether a sufficiently sized edge strip is available.

Protect the levelling compound layer from direct sunlight and draughts while it sets.

Important

Processing not below floor temperature of +15 °C and room temperature of +18 °C, as well as room humidity preferably between 40 % and 65 %, maximum 75 %. All information is based on approx. 20 °C and 50 % relative air humidity. Warm up all laying materials in due time in heated room.

When applying levelling compound in a layer thickness over 5 mm on calcium sulphate-bonded screeds, use only Wakol reaction primer such as WAKOL PU 280 Polyurethane Primer. Please consult the corresponding data sheet for further details.

The layer thickness permitted on mastic asphalt (IC10 and IC15) is max. 5 mm.

For applying levelling compound on wooden subfloors that are rigidly bolted or glued to the subfloor, only use WAKOL Z 626 Levelling Compound in a maximum of 6 mm.

Do not sand levelling compound before laying parquet in order to ensure the best possible adhesion.

When used as a floor covering, a suitable surface treatment must be applied.

We recommend the use of Loba products that are marked with the Connected Systems for levelling compounds.

Please contact the Application Technology department beforehand for details about the processing of the levelling compound when used as a floor covering.

We guarantee the uniform high quality of our products. All data is based on tests and many years of practical experience and refers to standardized conditions. The variety of materials used and the different construction site conditions, which lie beyond our control, preclude any claims based on this data. We therefore recommend making sufficient trials. Accompanying flooring manufacturer's instructions and the current national standard must be observed. We gladly provide technical advice.

This Technical Information of 21.09.2023 supersedes all previous versions.